



# Texturation of lead-free BaTiO<sub>3</sub>-based piezoelectric ceramics

A Ngueteu-Kamlo, F Levassort, M Pham Thi, Pascal Marchet

## ► To cite this version:

A Ngueteu-Kamlo, F Levassort, M Pham Thi, Pascal Marchet. Texturation of lead-free BaTiO<sub>3</sub>-based piezoelectric ceramics. Electroceramics XIV, Jun 2014, Bucarest, Romania. hal-01116537

**HAL Id: hal-01116537**

**<https://hal-unilim.archives-ouvertes.fr/hal-01116537>**

Submitted on 13 Feb 2015

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Texturation of lead-free BaTiO<sub>3</sub>-based piezoelectric ceramics

A. Ngueteu-Kamlo<sup>1</sup>, F. Levassort<sup>2</sup>, M. Pham Thi<sup>3</sup>, P. Marchet<sup>1</sup>

*1 Laboratoire de Science des Procédés Céramiques et de Traitements de Surface, UMR 7315 CNRS, Université de Limoges, Centre Européen de la Céramique, 12, rue Atlantis, F-87068 Limoges Cedex, France.*

*2 Université François Rabelais de Tours, GREMAN CNRS 734, 10 Boulevard Tonnellé, BP 3223, F-37032 TOURS Cedex 1, France*

*3 THALES Research & Technology France, Campus Polytechnique, 1, Av. Augustin Fresnel, F-91767 Palaiseau Cedex - France*

*Contact author: pascal.marchet@unilim.fr*

Nowadays, piezoelectric ceramics are integrated in a wide range of devices, in particular in ultrasonic applications (underwater sonar systems, medical imaging, non-destructive testing...). Most of them use Pb(Zr,Ti)O<sub>3</sub> (PZT). However, due to health care and environmental problems, lead content must be reduced in such applications [1]. Recent reviews demonstrated that few lead-free materials families can be considered: the alkaline-niobates (K<sub>0.5</sub>Na<sub>0.5</sub>NbO<sub>3</sub>), the alkaline-bismuth-titanates (Na<sub>0.5</sub>Bi<sub>0.5</sub>TiO<sub>3</sub>) and barium titanate based materials (BaTiO<sub>3</sub>) [2, 3]. One of the limitations of ceramic materials is their isotropic nature. This is the reason why texturation process has been developed in order to improve their properties in particular electromechanical parameters. The aim of the present study is thus to obtain textured BaTiO<sub>3</sub> based materials by using the templated grain growth process (TGG) and to measure their piezoelectric properties.

Nanosized BaTiO<sub>3</sub> powders were prepared by classical solid state route at relatively low temperature. BaTiO<sub>3</sub> templates of different morphologies were elaborated by a molten salts process. Dispersing agent, binder and plasticizer, the mixture of the templates and matrix particles was then dispersed in the appropriated solvent using non-aqueous formulation. The slurry was then tape-casted on plastic film. After drying, the green sheet was cut, stacked, thermo compressed and then sintered at the appropriated temperature. This process allowed obtaining highly-oriented materials with a texturation degree around 95%

(fig. 1), presenting  $K_t$  values around 35-40%, higher than for non-textured BaTiO<sub>3</sub> ceramics.




Fig. 1: X-ray diffraction diagram of (tetragonal) textured sample BaTiO<sub>3</sub> and (tetragonal) non-textured BaTiO<sub>3</sub> ceramic as reference.

**Acknowledgements:** The authors kindly acknowledge financial support from the French Research National Agency (ANR), project HYPERCAMPUS

[1] Directive 2002/95/EC, Official Journal of the European Union, 13.2.2003

[2] J. Rodel, W. Jo, T.P. Seidert, E-M. Anton, T. Granzow, D. Damjanovic, J. Am. Ceram. Soc. 92, 1153-1177, 2009

[3] P.K. Panda, J. Mater. Sci. 44, 5049-5062, 2009